

SOLYX® Glass Finishes

SX-1801 White Random Lines



Product Description

SOLYX® SX-1801 White Random Lines is a clear polyester film with a decorative line pattern in varying widths and shades of white. It is ideal for obscuring direct visibility while allowing light through.

Specifications

Specifications	
Product Code	SX-1801
Product Family	Geometric
Film Type	Polyester
Adhesive Type	Pressure-Sensitive
Usage	Interior
Available Width(s)	60" (1524mm)
Full Roll Length	100 linear feet
Thickness	2 mil
Visible Light Transmission	38% ASTM D 1003
UV Transmission	28%
Infra-Red Transmission	57%
Tensile strength	MD: 18 Kg/mm2 ASTM D 882
Tensile strength	TD: 23 Kg/mm2
Elongation	MD: 140 % ASTM D 882
At Break	TD: 105 %
Friction	0.25 uk ASTM D 1894
Coefficient	0.41 us ASTM D 1894
Surface roughness	0.220 um
Haze	60% ASTM D 1003
Gloss	37% ASTM D 523
Heat Shrinkage	MD: 2.9 % 150 Degree C – 30min
	TD: 0.3 %

Product Construction

Face Film

2 mil Polyester

Adhesive

0.8 to 1.0 mil, Acrylic, Pressure-Sensitive

Release Liner

Polypropylene, Silicone Coated

Product Details

 $SOLYX \otimes SX-1801$ White Random Lines is a clear, durable, polyester film with a decorative line pattern in varying widths and shades of white which runs down the length of the roll. It is recommended for application to interior, single- or double-pane, and exterior facing glass. It is ideal for privacy, decorative, or architectural applications.

Flammability Rating

This product meets ASTM E84 and is classified as Class A as defined in NFPA 101, Life Safety Code®.

LEED Credit EQ 4.1 Low Emitting Materials, Adhesives & SealantsThis product has zero VOC content according to 40 CFR 59, Subpart D (EPA method 24).

Features

Dimensional Stability: Good

Temperature Ranges: Minimum application temperature is +40°F. Service temperature range is -40°F to +250°F.

Adhesion: To stainless steel -400z. / in. PSTC-1 with 24-hr dwell at 70° F and 50% relative humidity, typical values. Individual values may vary.

Water Resistance: Has limited immersion resistance - test specific application.

Humidity Resistance: Good

Storage Stability: 2-yr shelf life when stored at 70°F and 50% relative humidity.

Installation and Warranty

Installation

Installation should be in accordance with the manufacturer's installation instructions. It is applied using the same tools and techniques used for installing window tinting films.

Warranty

This SOLYX® product will be free from defects in material and manufacture for a period of five (5) years from the date of installation. See warranty information for specific details.

Product Distribution and Contact Information

Distribution

 $SOLYX @ \ \, Decorative \ \, Films \ \, are \ \, available \ \, through \ \, authorized \\ Installing \ \, Dealers, \ \, Distributors \ \, or \ \, directly \ \, from \ \, Decorative \ \, Films, \ \, LLC. \\ Samples \ \, submitted \ \, upon \ \, request. \\$

Contact Information

Decorative Films, LLC Tel: 888-657-5224 www.decorativefilm.com